

**THE EFFECT OF CALCINATION TEMPERATURE ON THE STRUCTURE AND
PHOTOCATALYTIC ACTIVITY OF CARBON-DOPED TITANIUM DIOXIDE
PREPARED VIA SOL-GEL ROUTE**

NOR ARBANI BINTI SEAN

UNIVERSITI TEKNOLOGI MALAYSIA

THE EFFECT OF CALCINATION TEMPERATURE ON THE STRUCTURE
AND PHOTOCATALYTIC ACTIVITY OF CARBON-DOPED TITANIUM
DIOXIDE PREPARED VIA SOL-GEL ROUTE

NOR ARBANI BINTI SEAN

A report submitted in partial fulfilment of the
requirements for the award of the degree of
Master of Science (Chemistry)

Faculty of Science
Universiti Teknologi Malaysia

FEBRUARY 2017

*Specially dedicated to my beloved
MOM, Miskiah
DAD, Sean
SISTERS, Kartini and Tumirah
BROTHER, Mohd Khairul
Thank you very much for the prayer, love and support.*

ACKNOWLEDGEMENT

In the name of Allah, the Most Gracious and the Most Merciful.

Alhamdulillah, praise to Allah, with all His kindness and mercy, had gave me the chance to complete this thesis with a success. I would like to express special thanks to my supervisor, Prof. Dr. Hadi Nur for the valuable advices and guidance throughout this project. This project could not have completed without his guidance.

I would like to thanks all the lecturers in the Department of Chemistry, Faculty of Science, Universiti Teknologi Malaysia. Thanks for enhance my knowledge in Chemistry and these knowledge really helps in accomplishing this project.

Besides, I would like to express thousands of appreciations to all laboratory assistants for providing me technical support and guidance throughout my project.

Last but not least, I would like to thank my beloved family, my mother (Miskiah binti Likan), my father (Sean bin Rani) and my siblings for giving me endless prayer, love and support and also my fellow friends for being supportive and considerate when I was in need for their help.

Thank you.

ABSTRACT

The outstanding accomplishment by Fujishima and Honda (1972) on the discovery of photocatalytic water splitting by titanium dioxide (TiO_2) electrodes results in the extensive study of TiO_2 for air and water purification for environmental applications. Despite all the advantages provided from TiO_2 compared to other semiconductor photocatalysts, its two main concern issues, which are large band gap energy (E_g) and high recombination rate of photogenerated electrons (e^-) and holes (h^+) pairs, restraint its usage in practical applications. Therefore, the development of visible light active TiO_2 become the challenge of researchers in the field of semiconductors photocatalysis. This study has been designated to the development of modified TiO_2 photocatalyst to enhance its photocatalytic activity into visible range and increase the charge carrier separation for more beneficial applications by carbon doping modification. Carbon-doped TiO_2 (C- TiO_2) nanoparticles with amorphous, anatase and mixed anatase/rutile phase were successfully synthesized via a simple and low-cost sol-gel route based on the self-assembly technique exploiting polyoxyethylenesorbitan monooleate (Tween 80) as a carbon source and calcined at 300-600 °C. The as-prepared powders were characterized by attenuated total reflectance spectra Fourier transform infrared spectroscopy (ATR-FTIR), diffuse reflectance ultraviolet-visible spectroscopy (DR UV-Vis), X-ray diffraction (XRD), scanning electron microscopy (SEM), photoluminescence (PL), and UV-Visible spectrophotometry (UV-Vis). With prolonged calcination temperature, the crystallite size and E_g were increased and the level of carbon doping decreased. All the nanoparticles showed high absorption in UV and visible light region. This is due to the reduction of E_g and the formation of sub-band observed by UV-Vis and PL spectrum, respectively. The formation of sub-band widens the absorption towards the visible light region. The potential of using the synthesized C- TiO_2 nanoparticles for photocatalytic environment remediation was demonstrated by the degradation of phenolphthalein (PHP) under UV and visible light irradiation. These photocatalytic activities were attributed to the level of carbon doping and crystallite structure. Carbon acts as an electron-trapping agent and causes structural defects as observed by PL spectrum. Obviously, it produces a low rate of recombination of e^-/h^+ as observed by PL spectroscopy which will have high separation of charge carrier and better performance of the photocatalytic activity. It was revealed that the amorphous C- TiO_2 is inert and the samples calcined from 400 °C to 600 °C have a decreasing trend of photocatalytic activity with the increased in size of nanoparticles. Among all, C- TiO_2 photocatalyst calcined at 400°C was found to be more effective with an ideal amount of carbon, the presence of hydroxyl group, better crystallinity of amorphous-anatase mixture, and the existence of sub-band which reduces the band gap energy. Thus, exhibits high degradation percentage of PHP under UV and visible light irradiations, leading to as much as 3.7 and 11.89 % respectively. As a result, carbon doping modification is an appropriate strategy to enhance the photocatalytic activity by improving visible-light absorption and e^-/h^+ separation.

ABSTRAK

Pencapaian cemerlang yang diperolehi oleh Fujishima dan Honda (1972) mengenai penemuan fotomangkin pembahagi air pada elektrod titanium dioksida (TiO_2) telah menyebabkan banyak kajian mengenai TiO_2 dalam aktiviti pembersihan udara dan air untuk aplikasi alam sekitar. Walaupun TiO_2 memberikan banyak kelebihan berbanding fotomangkin semikonduktor yang lain, dua permasalahan utamanya iaitu tenaga jurang jalur (E_g) yang besar dan kadar penggabungan semula pasangan elektron yang terhasil (\bar{e}) dan lubang (h^+) yang tinggi telah menyebabkan penggunaannya di dalam aplikasi praktikal terhad. Oleh itu, penghasilan TiO_2 yang aktif di bawah sinaran cahaya nampak menjadi cabaran kepada para penyelidik di dalam bidang fotopemangkinan semikonduktor. Kajian tersebut meliputi penghasilan fotomangkin TiO_2 yang diubahsuai untuk meningkatkan aktiviti fotopemangkinan di bawah sinaran cahaya nampak dan meningkatkan kadar pemisahan pembawa cas untuk aplikasi yang lebih bermanfaat melalui pendopan karbon. Nanopartikel TiO_2 yang didopkan dengan karbon (C- TiO_2) yang berfasa amorfus, anatase dan campuran fasa anatase/rutil telah berjaya disintesis melalui kaedah sol-gel yang mudah dan berkos rendah berdasarkan teknik pemasangan diri dengan mengeksploitasi polioxietilenasorbitan monooleate (Tween 80) sebagai sumber karbon dan dikalsin pada suhu 300-600 °C. Serbuk yang terhasil dicirikan dengan menggunakan spektroskopi infra-merah transformasi Fourier (FTIR), spektroskopi pantulan serakan ultralembayung (DR-UV), pembelauan X-Ray (XRD), mikroskopi pengimbas elektron (SEM) spektroskopi foropendarcahaya (PL), dan juga spektroskopi ultralembayung-cahaya nampak (UV-Vis). Dengan suhu pengkalsinan yang berpanjangan, saiz kristal dan E_g telah meningkat dan tahap karbon yang didopkan berkurangan. Kebanyakan nanopartikel menunjukkan penyerapan yang tinggi di bawah sinaran UV dan cahaya nampak. Ini adalah disebabkan oleh pengurangan E_g dan pembentukan beberapa jalur tambahan sepertimana yang dapat dilihat pada keputusan spektrum UV-Vis dan PL. Potensi nanopartikel C- TiO_2 dalam pemulihan alam sekitar dengan menggunakan fotomangkin telah dibuktikan melalui degradasi fenofalein (PHP) di bawah sinaran UV dan cahaya nampak. Aktiviti fotopemangkinan yang bertambah baik telah dikaitkan dengan tahap karbon yang didopkan dan struktur kristal itu sendiri. Karbon bertindak sebagai agen pemerangkap elektron dan menyebabkan kecacatan struktur seperti yang diperhatikan di dalam spektrum PL. Jelas sekali, ia menghasilkan kadar penggabungan semula \bar{e}/h^+ yang rendah seperti yang diperhatikan di dalam spektroskopi PL yang mempunyai kadar pemisahan pembawa cas yang tinggi dan aktiviti fotopemangkinan yang lebih baik. Ia telah membuktikan bahawa amorfus C- TiO_2 adalah lengai dan sampel yang dikalsin dari suhu 400 °C sehingga 600 °C mempunyai penurunan aktiviti fotopemangkinan dengan peningkatan dalam saiz nanopartikel. Antara semua, fotomangkin C- TiO_2 yang dikalsin pada 400 °C didapati lebih berkesan dengan jumlah yang ideal bagi karbon, kehadiran kumpulan hidroksil, penghabluran yang lebih baik, dan kewujudan jalur tambahan yang mengurangkan tenaga jurang jalur. Oleh itu, mempamerkan peratusan kemerosotan PHP yang tinggi di bawah sinaran UV dan cahaya nampak, yang membawa kepada sebanyak 3.7 dan 11.89 % masing-masing. Kesimpulannya, pengubahsuaian pendopan karbon adalah salah satu strategi yang sesuai bagi meningkatkan aktiviti fotopemangkinan dengan menggalakkan penyerapan cahaya nampak dan pemisahan \bar{e}/h^+ .

TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	SUPERVISOR DECLARATION	ii
	AUTHOR'S DECLARATION	iii
	DEDICATION	iv
	ACKNOWLEDGEMENT	v
	ABSTRACT	vi
	ABSTRAK	vii
	TABLE OF CONTENTS	viii
	LIST OF TABLE	xi
	LIST OF FIGURE	xii
	LIST OF SCHEME	xv
	LIST OF ABBREVIATIONS	xvi
 1	 INTRODUCTION	 1
	1.1 Background of Study	1
	1.2 Statement of Problem	4
	1.3 Objectives of Study	5
	1.4 Scope of Study	6
	1.5 Hypothesis of Study	6
	1.6 Significance of Study	6
 2	 LITERATURE REVIEW	 8
	2.1 Photocatalysis	8
	2.2 Titanium Dioxide (TiO ₂)	13
	2.2.1 TiO ₂ Photocatalyst	13
	2.2.2 Modification of TiO ₂ Photocatalyst	17

2.2.2.1	Carbon-Doped TiO ₂ Photocatalyst	18
2.2.2.2	Photoactivation Mechanism of Carbon-Doped TiO ₂ Photocatalyst	19
2.3	Theory of Carbon-Doped TiO ₂	21
2.3.1	Structural Properties of Carbon-Doped TiO ₂	21
2.3.2	Electronic Band Structures of Carbon- Doped TiO ₂	23
2.4	Sol-Gel Methods	26
2.4.1	Carbon-Doped TiO ₂ Synthesized via Sol-Gel Route	28
2.5	Polyoxyethylenesorbitan Monooleate Surfactant	29
2.6	Phenolphthalein	30
3	RESEARCH METHODOLOGY	32
3.1	Introduction	32
3.2	Chemicals and Reagents	34
3.3	Characterization	34
3.4	Preparation of Photocatalyst	35
3.4.1	Preparation of Carbon-Doped TiO ₂ And Undoped TiO ₂ Photocatalyst	37
3.5	Preparation of Solution	37
3.5.1	Preparation of Stock Solution of Phenolphthalein	37
3.6	Photoreactor System	37
3.7	Photocatalytic Activity	39
3.7.1	Photodegradation of Phenolphthalein Under UV Light Irradiation	39
3.7.2	Photodegradation of Phenolphthalein Under Visible Light Irradiation	39

4	RESULTS AND DISCUSSIONS	41
4.1	Introduction	41
4.2	Synthesis of C- TiO ₂ at Different Calcination Temperature	41
4.3	Surface Chemical Analysis of C-Doped TiO ₂	42
4.4	Crystallographic Study of C-Doped TiO ₂	45
4.5	Morphological Properties of C-Doped TiO ₂	49
4.6	Optical Properties of C-Doped TiO ₂	51
4.7	Photocatalytic Activity	61
4.7.1	Adsorption-Desorption Equilibrium Throughout Degradation	63
4.7.2	Photocatalytic Activity under UV and Visible Light	64
4.8	Summary	68
5	CONCLUSION AND SUGGESTIONS	69
5.1	Conclusion	69
5.2	Future Works	70
	REFERENCES	71

LIST OF TABLE

TABLE NO.	TITLE	PAGE
2.1	The band position of some common semiconductor photocatalysts in aqueous solution	12
2.2	Properties of titanium dioxide in anatase and rutile crystal	16
2.3	Several C-TiO ₂ photocatalysts synthesized via a sol-gel route	29
2.4	List of non-ionic surfactants available in the industry	30
4.1	Size comparisons between reference anatase TiO ₂ , undoped TiO ₂ and its carbon-doped TiO ₂ calcined at different calcination temperature	48
4.2	Energy gap of samples as calculated from optical absorption spectra	53
4.3	Calculated conduction and valence band edge positions of TiO ₂ based photocatalysts by using Mulliken electronegativity	55
4.4	Energy gap of samples as calculated from PL spectra	60

LIST OF FIGURE

FIGURE NO.	TITLE	PAGE
1.1	Spectrum of solar irradiance, I , compared with that of a 5770 K blackbody radiator. The blue dotted line shows the spectrum of radiation reaching the surface of the Earth	2
2.1	Energy band in solids (a) insulator, (b) semiconductor and (c) conductor	10
2.2	Process occurring on bare TiO_2 particles after UV excitation	11
2.3	Bulk structures of titanium dioxide (a) anatase, (b) rutile and (c) brookite	14
2.4	The tetragonal bulk unit cell of (a) anatase and (b) rutile dimension	15
2.5	Mechanism of TiO_2 photocatalysis ($h\nu_1$) pure TiO_2 ; ($h\nu_2$) metal-doped TiO_2 and ($h\nu_3$) nonmetal-doped TiO_2	18
2.6	Proposed schematic illustration of the photocatalytic mechanism of C- doped TiO_2 nanoparticles under visible light irradiation	20
2.7	Partial geometry of TiO_2 models for (a) one substitutional C atom to O ($\text{C}_{\text{S-O}}$), (b) one substitutional C atom to Ti ($\text{C}_{\text{S-Ti}}$), (c) one interstitial C atom (C_{I}), and (d) one interstitial C atom nearby an oxygen vacancy ($\text{C}_{\text{I}}+\text{V}_{\text{O}}$) in the anatase TiO_2 supercell.	22
2.8	(a) DOS and (b) PDOS for 96 atoms anatase supercell with C replaced O	24
2.9	The calculated (a) TDOS and (b) PDOS for C	25

	mono-doping of anatase C@O ₁	
2.10	Model for the anatase C-doping Ti ₅₉ O ₁₀₀ at different substitutional	25
2.11	Schematic illustration of an (a) amphiphile component and (b) the orientation of amphiphile at the phase boundary	29
2.12	Structure of polyoxyethylenesorbitan monooleate (Tween 80)	30
2.13	Structural formula of phenolphthalein	31
3.1	A flow chart for the photocatalysts preparation, characterization and their photocatalytic activity	33
3.2	Scheme summarized the procedure for the TiO ₂ -based photocatalyst	36
3.3	Test system design under (a) visible light and (b) UV light irradiation	38
4.1	Photograph of (a) Reference, (b) Undoped TiO ₂ , (c) C-TiO ₂ -300, (d) C-TiO ₂ -400, (e) C-TiO ₂ -500 and (f) C-TiO ₂ -600	42
4.2	FTIR spectra of (a) reference, undoped TiO ₂ and C-TiO ₂ -400 and (b) all the C-TiO ₂ samples	44
4.3	XRD pattern of nanocrystalline reference anatase	46
4.4	XRD pattern of prepared TiO ₂ and C-TiO ₂ samples at different calcination temperature	47
4.5	SEM micrographs of (a) reference anatase TiO ₂ , as-prepared (b) undoped TiO ₂ , (c) C-TiO ₂ -300, (d) C-TiO ₂ -400, (e) C-TiO ₂ -500 and (f) C-TiO ₂ -600	50
4.6	(a) UV-vis diffuse reflectance spectra of reference anatase TiO ₂ , undoped TiO ₂ and C-TiO ₂ calcined at a different temperature. (b) The plot of (FR _x hν) ² versus hν using the Kubelka-Munk function and the Tauc equation	52
4.7	The proposed conduction and valence band edge position of TiO ₂ based photocatalysts	55
4.8	The photoluminescence spectra for (a) Reference	57

	anatase TiO_2 , Undoped TiO_2 and Doped TiO_2 calcined at 400°C , and (b) C- TiO_2 calcined at different temperatures	
4.9	The proposed illustration of the electrons excitation of the prepared photocatalysts	60
4.10	The (a) UV-Vis spectra of PHP solutions with different concentrations, and a (b) calibration curve for phenolphthalein absorption peak at 228 nm in UV-Vis spectrum	62
4.11	Variation of light absorbance of PHP with the presence of C- TiO_2 -400 photocatalyst under different light irradiations (I: Adsorption, II: Desorption, and III: Degradation)	63
4.12	Percent of degradation (%) of PHP in the presence of a different catalyst under (a) UV and (b) visible light radiation	65
4.13	Imperfections of the crystal structure	66

LIST OF SCHEME

SCHEME NO.	TITLE	PAGE
2.1	Mid-gap states in the semiconductor band gap after C replaced O	24
2.2	A typical procedure in preparing TiO ₂ based photocatalyst via sol-gel method	27
2.3	The synthesis of phenolphthalein	31

LIST OF ABBREVIATION

%D	- Percent of degradation
ATR	- Attenuated total reflectance
C	- Carbon
CB	- Conduction band
DFT	- Density functional theory
DR	- Diffuse reflectance
e⁻	- Electron
E_g	- Band gap energy
FTIR	- Fourier transform infrared spectroscopy
h⁺	- Positive hole
nm	- Nanometre
OH	- Hydroxyl
OV	- Oxygen vacancies
P	- Pollutant
PHP	- Phenolphthalein
PL	- Photoluminescence
POPs	- Persistent organic pollutants
SEM	- Scanning electron microscope
TiO₂	- Titanium dioxide
TTIP	- Titanium tetraisopropoxide
Tween 80	- Polyoxyethylenesorbitan monooleate
UV-Vis	- Ultraviolet-visible
VB	- Valence band
XRD	- X-ray diffraction

CHAPTER 1

INTRODUCTION

1.1 Background of Study

Nowadays, the crisis brought by ‘greenhouse effect’ has become a great issue in many countries. This is due to the combustion of the toxic organic pollutants released from industries into water, air, and soil. Since the first discovery of photocatalytic water splitting on titanium dioxide (TiO₂) electrodes in 1972 by Fujishima and Honda, scientists have done many studies on the photocatalytic activity of TiO₂ to deal with these challenges (Fujishima and Honda, 1972).

TiO₂, which is among the most basic materials in our daily life, represents an effective photocatalyst for water and air purification (Fujishima *et al.*, 2000). Additionally, it is also associated with self-cleaning technology that is responsible for the development of green living environment (Zhang Li, 2013). The photocatalyst is the substance which can absorb light quanta of appropriate wavelengths depending on the band structure (Banerjee *et al.*, 2015). The process in which this substance is being utilized in the chemical reaction is called photocatalysis (Etacheri *et al.*, 2015). In order to develop an efficient photocatalyst, the catalyst should satisfy high stability in extreme environment, photoactive, photo-stable and low cost (Mills *et al.*, 1993; Pelaez *et al.*, 2012a).

The most commonly used photocatalysts are metal oxides such as TiO₂, ZnO, Fe₂O₃, WO₃, and SnO₂ (Etacheri *et al.*, 2015; Fujishima and Honda, 1972; Santhi *et*

al., 2016; Tayyebi *et al.*, 2016; Uddin *et al.*, 2016; Wang *et al.*, 2016). Among all, TiO_2 is a widely used semiconductor since it provides all the special characteristics in all the aspects mentioned above.

However, despite all the advantages provided by TiO_2 compared to other semiconductor photocatalysts, there are two main concern issues that restrain its usage in practical applications. Firstly, TiO_2 has a large band gap, which is 3.2 eV, and require UV light for the excitation of electrons to take place. This has limited its photocatalytic activity under solar energy or visible light, which is the most abundant light in the electromagnetic spectrum. Figure 1.1 shows the solar spectrum in different spectral irradiance. Secondly, TiO_2 possesses fast electrons (e^-) and holes (h^+) recombination that will decrease the photocatalytic activity. Therefore, for more beneficial photocatalytic applications, it is essential to develop a system that producing TiO_2 with high efficiency under visible light region.




Figure 1.1: Spectrum of solar irradiance, I , compared with that of a 5770 K blackbody radiator. The blue dotted line shows the spectrum of radiation reaching the surface of the Earth (Gray *et al.*, 2010; Lean, 1991).

Many studies have been designated to improve the production of highly reactive TiO₂ under visible light. Visible light activated TiO₂ photocatalyst can be prepared by using dye sensitization (Saïen and Mesgari, 2016), noble metal loading (Kmetyko *et al.*, 2016), transition metal addition (Yadav *et al.*, 2016) and non-metal doping (Wang *et al.*, 2012). Noble metals such as Ag, Au, Pt and Pd or the combinations of these metals with TiO₂ were of the particular interest due to its well-known properties of improving the photocatalytic efficiency of TiO₂ under visible light irradiation. They can act as an electron trap and delay the recombination of the e⁻/h⁺ pair through the promotion of the interfacial charge transfer (Fagan *et al.*, 2016). However, due to some problems associated with metal doping, which the metals introduced were not incorporated into the TiO₂ framework, and block the reaction sites on the TiO₂ surface, non-metal elements such as carbon and nitrogen were studied comprehensively (Zhu *et al.*, 2006).

The use of non-metal as doping material such as nitrogen (Than *et al.*, 2017), sulfur (Seo *et al.*, 2016), fluorine (Zhang *et al.*, 2016), iodine (Wang *et al.*, 2016) and carbon (Zhang *et al.*, 2016) is able to control the stability of the TiO₂ and also enhance the visible light irradiation. Carbon was found to be more efficient compared to most of the non-metal elements due to its useful properties. Carbon has high electrical and thermal conductivity, high chemical stability, low thermal expansion coefficient, high lubricity, light weight, possibility to have various pores, non-toxic and radiation resistant (Zaleska, 2008).

Since the first report on carbon-modified TiO₂ reported by Kisch and co-workers, many physical and chemical investigations were done for the synthesis of carbon-doped titanium dioxide (Sakthivel and Kisch, 2003). Its ability to narrow down the band gap of TiO₂ significantly increases the photocatalytic activity towards visible light irradiation compared to pure anatase TiO₂ (Zhang *et al.*, 2016).

Previously, it has been reported that the use of self-assembly surfactant-based sol-gel methods is effective ways to design the structural properties of TiO₂ from molecular precursors (Choi *et al.*, 2006; Zhu *et al.*, 2006). Hydrocarbon surfactants

were added to act as carbon doping precursor to enhance the photocatalytic activity of TiO₂ under visible light.

Regardless of the numerous studies based on visible light active carbon-doped TiO₂ photocatalyst, the relationship between the synthesis method, optical properties, structural properties and the efficiency of the visible light photocatalytic activity remain controversial and still need to be investigated. Thus, in this research, a simple and low-cost process was established for the synthesis of visible light active C-TiO₂ photocatalysts via the sol-gel route of precursor titanium tetraisopropoxide (TTIP), at different calcination temperature of 300 °C to 600 °C for 3 hours.

1.2 Statement of Problem

The utilization of TiO₂ photocatalyst in air and water treatment promises better views as it provides high efficiency in the degradation of organic pollutants (Zaleska, 2008). However, its wide scale of practical application is limited by its large band gap energy (3.2 eV), which allows the only small amount of solar energy to be used. Also, the high recombination rate of photogenerated e⁻ and h⁺ that occurs reduces its photocatalytic activity efficiency, which resulting in low degradation percentage of organic pollutants. Previously, these problems had been solved by developing an effective TiO₂ photocatalyst with a reduced band gap and make it reactive under visible light region. However, most of the techniques used to synthesize the material are expensive, hard to control and chemically unstable (Pelaez *et al.*, 2012). In order to overcome all these problems, a mild and easily controlled sol-gel technique had been chosen to be the promising way to develop highly reactive C-doped TiO₂ under visible light irradiation, with the utilization of polyoxyethylenesorbitan monooleate (Tween 80) surfactant as a carbon source, and titanium tetraisopropoxide (TTIP) as the TiO₂ precursor.

Tween 80 was selected as carbon source material since it contain high number of carbon, easy to obtain, cheap, and highly miscible in aqueous solution compared to other carbon source material, such as carbon nanotube (CNT) (Wongaree *et al.*, 2015), regenerated cellulose membrane (RCM) (M.A. Mohamed *et al.*, 2016), and resorcinol-furfural (Shao *et al.*, 2013). Besides that, C-doping promises a high number of photogenerated electrons and defect sites, which able to trap mobile electrons and lower the recombination rate of e^-/h^+ , thereby resulted in the high photocatalytic activity of TiO_2 photocatalysts.

The effect of calcination temperature towards the synthesized C- TiO_2 was characterized by several analytical instruments. The surface bonding of C- TiO_2 was first studied using attenuated total reflectance Fourier transform infrared spectroscopy (ATR-FTIR), while the morphological and physical properties were characterized by scanning electron microscope (SEM), and X-ray diffraction (XRD) spectrometer. The optical properties were characterized using diffuse reflectance ultraviolet-visible (DR UV-Vis) spectrometer and photoluminescence (PL) spectrometer.

1.3 Objectives of Study

The objectives of this study are:

- To synthesize carbon-doped TiO_2 photocatalyst by the self-assembly surfactant sol-gel method at different calcination temperature.
- To study the effect of calcination temperature of the prepared carbon-doped TiO_2 by using ATR-FTIR, DR UV-Vis, SEM, XRD, and PL.
- To evaluate the photocatalytic performance of carbon-doped TiO_2 under UV and visible light irradiances by using DR UV-Vis spectroscopy for phenolphthalein degradation.

1.4 Scope of Study

The research covered the synthesis of C-TiO₂ photocatalyst via self-assembly surfactant-based sol-gel method at different calcination temperature. The non-ionic surfactant (Tween 80) was used as the source of carbon material. The photocatalyst was characterized further using XRD, SEM, DR-UV spectrophotometer, ATR-FTIR, and PL. The photodegradation of phenolphthalein was carried out in the presence of UV and visible light and was monitored using diffuse reflectance ultraviolet-visible (DR UV-Vis) spectrometer.

1.5 Hypothesis of Study

Non-metal doping has proved to be an efficient way in modifying the structure of TiO₂ photocatalysts so that it can easily absorb visible light which is abundant in the solar irradiation. It is also responsible for reducing the band gap energy by the formation of sub-band between the valence band and conduction band. In addition, through this doping modification, the rate of recombination of e^-/h^+ has been reported to decrease as the defect sites created by the carbon-doping act as electron trapping agent that delay the rate of e^-/h^+ recombination. This is useful for the oxidation of organic pollutants in the environment. Therefore, non-metal doping seems to be an effective way in enhancing photocatalytic activity of TiO₂ photocatalysts.

1.6 Significant of Study

The development of TiO₂ photocatalysts has led to its usage in many fields including in the degradation of organic pollutants in waste and wastewater treatment. Despite all the advantages provided by TiO₂ photocatalysts, some modifications have been made to increase its efficiency on the photocatalytic activity and the most

prominent method to be used is by carbon-doping. Therefore, this research will provide an understanding of the synthetic method used to develop C-doped TiO_2 photocatalyst which relates to their optical and structural properties. This photocatalyst will ultimately reduce the band gap of TiO_2 as well as the rate of e^-/h^+ recombination. As a consequence, this would drive the use of photocatalyst which only use the sunlight for any reaction to occur without the use of any conventional method that is hard to control and time-consuming.

REFERENCES

- Akpan, U. G., & Hameed, B. H. (2010). The Advancements in Sol–Gel Method of Doped-TiO₂ photocatalysts. *Applied Catalysis A : General*. 375: 1–11.
- Albetran, H., Connor, B. H. O., & Low, I. M. (2016). Effect of Calcination on Band Gaps for Electrospun Titania Nano Fibers Heated in Air – Argon Mixtures. *JMADE*. 92: 480–485.
- Alias, S. H., Nur, H., Sahnoun, R., Dittrich, T., & Baharvand, A. (2017). The Effect of the Structural Distortions and Carbon Doping on the Electronic Properties of Titanium Dioxide Anatase. *Personal Communication*.
- An, Y., de Ridder, D. J., Zhao, C., Schoutteten, K., Bussche, J. Vanden, Zheng, H., Vanhaecke, L. (2016). Adsorption and Photocatalytic Degradation of Pharmaceuticals and Pesticides by Carbon-Doped TiO₂ Coated on Zeolites under Solar Light Irradiation. *Water Science and Technology*. 73: 12.
- Anaukwu, C. G., Ezemba, C. C., Anakwenze, V. N., Agu, K. C., Nwankwegu, A. S., Okeke, B. C., & Awah, N. S. (2016). Influence Of Anionic, Cationic And Non-Ionic Surfactants On Growth Of Hydrocarbon Utilizing Bacteria. *American Journal of Current Microbiology*. 4(1): 10–16.
- Asahi, R., Morikawa, T., Ohwaki, T., Aoki, K., & Taga, Y. (2001). Visible Light Photocatalysis in Nitrogen-Doped Titanium Oxides. *Science*. 293: 269-271.
- B. Lavand, A., & S. Malghe, Y. (2015). Nano Sized C-Doped TiO₂ As a Visible Light Photocatalyst for the Degradation of 2,4,6- Trichlorophenol. *Advanced Materials Letters*. 6(8): 695–700.
- Banerjee, S., Dionysiou, D. D., & Pillai, S. C. (2015). Self-cleaning Applications of TiO₂ by Photo-Induced Hydrophilicity and Photocatalysis. *Applied Catalysis B: Environmental*. 176-177: 396–428.

- Bard, A. J., & Fox, M. A. (1995). Artificial Photosynthesis: Solar Splitting of Water to Hydrogen and Oxygen. *Accounts of Chemical Research*. 28(3): 141–145.
- Braun, J. H., Baidins, A., & Marganski, R. E. (1992). TiO₂ Pigment Technology: A review. *Progress in Organic Coatings*. 20(2): 105–138.
- Cai, J., Xin, W., Liu, G., Lin, D., & Zhu, D. (2015). Effect of Calcination Temperature on Structural Properties and Photocatalytic Activity of Mn-C-Codoped TiO₂. 19(2): 401–407.
- Carp, O., Huisman, C. L., & Reller, A. (2004). Photoinduced reactivity of titanium dioxide. *Progress in Solid State Chemistry*. 32(1): 33–177.
- Cheng, M., Zeng, G., Huang, D., Yang, C., Lai, C., Zhang, C., & Liu, Y. (2017). Advantages and Challenges of Tween 80 Surfactant-Enhanced Technologies for the Remediation of Soils Contaminated with Hydrophobic Organic Compounds. *Chemical Engineering Journal*. 314: 98–113.
- Choi, H., Kim, Y. J., Rajender S. Varma, A., & Dionysiou, D. D. (2006). Thermally Stable Nanocrystalline TiO₂ Photocatalysts Synthesized via Sol–Gel Methods Modified with Ionic Liquid and Surfactant Molecules. *Chemistry of Materials*. 18(22): 5377–5384.
- Choi, J., Song, S., Hörantner, M. T., Snaith, H. J., & Park, T. (2016). Well-Defined Nanostructured, Single-Crystalline TiO₂ Electron Transport Layer for Efficient Planar Perovskite Solar Cells. *ACS Nano*. 10(6): 6029–6036.
- Choudhury, B., & Choudhury, A. (2013). Tailoring luminescence properties of TiO₂ nanoparticles by Mn doping. *Journal of Luminescence*. 136: 339–346.
- Choudhury, B., Dey, M., & Choudhury, A. (2014). Shallow and Deep Trap Emission and Luminescence Quenching of TiO₂ Nanoparticles on Cu Doping. *Applied Nanoscience*. 4(4): 499–506.
- Chuang, H., & Chen, D. (2009). Fabrication and Photocatalytic Activities in Visible and UV Light Regions of Ag@TiO₂ and NiAg@TiO₂ Nanoparticles. *Nanotechnology*. 20: 10.
- Ciftci, G., Durmus, M., Senkuytu, E., & Kılıc, A. (2009). Structural and

- Fluorescence Properties of Phenolphthalein Bridged Cyclotriphosphazatrienes. *Spechtrochimica Acta A: Molecular and Biomolecular Spectroscopy*.74: 881-886.
- Daniel, M., Luna, G. De, Lin, J. C., Jane, M., Gotostos, N., & Lu, M. (2016). Photocatalytic Oxidation of Acetaminophen Using Carbon Self-Doped Titanium Dioxide. *Sustainable Environment Research*, 1–7.
- Denkov, N. D., & Tcholakova, S. (2010). *Surfactants – Classification, Surfactants features and Applications features*. Sofia University, Bulgaria: Lecture Notes. 12–13.
- Diebold, U. (2003). The Surface Science of Titanium Dioxide. *Surface Science Reports*. 48(5-8): 53–229.
- Dong, P., Pei, H., Zhang, Q., & Wang, Y. (2014). Density Functional Study of X Monodoped and Codoped (X = C , N , S , F) Anatase TiO₂. *Computational Materials Science*. 93: 1-5.
- Etacheri, V., Di Valentin, C., Schneider, J., Bahnemann, D., & Pillai, S. C. (2015). Visible-Light Activation of TiO₂ Photocatalysts: Advances in Theory and Experiments. *Journal of Photochemistry and Photobiology C: Photochemistry Reviews*. 25: 1–29.
- Fagan, R., McCormack, D. E., Dionysiou, D. D., & Pillai, S. C. (2016). A Review of Solar and Visible Light Active TiO₂ Photocatalysis for Treating Bacteria, Cyanotoxins and Contaminants of Emerging Concern. *Materials Science in Semiconductor Processing*. 42: 2–14.
- Fujishima, A., & Honda, K. (1972). Electrochemical Photolysis of Water at a Semiconductor Electrode. *Nature*, 238(5358): 37–38.
- Fujishima, A., Rao, T. N., & Tryk, D. A. (2000). Titanium dioxide photocatalysis. *Journal of Photochemistry and Photobiology C: Photochemistry Reviews*. 1: 1-21.
- Gaber, A., Abdel Rahim, M. A., Abdel Latief, A. Y., & Abdel Salam, N. (2014). Influence of Calcination Temperature on the Structure and Porosity of

- Nanocrystalline SnO₂ Synthesized by a Conventional Precipitation Method. *International Journal of Electrochemical Science*. 9: 81-95.
- Geng, W., Liu, H., & Yao, X. (2013). Enhanced Photocatalytic Properties of Titania–Graphene Nanocomposites: A Density Functional Theory Study. *Physical Chemistry*. 15: 6025–6033.
- Gray, L. J., Beer, J., Geller, M., Haigh, J. D., Lockwood, M., Matthes, K. White, W. (2010). Solar Influences on Climate. *Reviews of Geophysics*. 48(4).
- Haart, L. De, Vries, A. De, & Blasse, G. (1985). On the Photoluminescence of Semiconducting titanates Applied in Photoelectrochemical Cells. *Journal of Solid State Chemistry*. 59: 291.
- Hashimoto, K., Irie, H., & Fujishima, A. (2005). TiO₂ Photocatalysis: A Historical Overview and Future Prospects. *Japanese Journal of Applied Physics*. 44: 12.
- Higaki, R. S., & Philp, W. M. S. (1976). A Study of the Sensitivity, Stability and Specificity of Phenolphthalein as an Indicator Test for Blood. *Canadian Society of Forensic Science Journal*. 9(3): 97–103.
- Hoffmann, M. R., Martin, S. T., Choi, W., & Bahnemann, D. W. (1995). Environmental Applications of Semiconductor Photocatalysis. *Chemical Reviews*. 95(1): 69–96.
- Hu, Y., Tsai, H., & Huang, C. (2003). Effect of brookite phase on the anatase–rutile transition in titania nanoparticles. *Journal of the European Ceramic Society*. 23: 691–696.
- Iijima, K., Goto, M., Enomoto, S., Kunugita, H., & Ema, K. (2008). Influence of Oxygen Vacancies on Optical Properties of Anatase TiO₂ Thin Films. *Journal of Luminescence*. 128(5-6): 911-913.
- Irie, H., Watanabe, Y., & Hashimoto, K. (2003). Carbon-Doped Anatase TiO₂ Powders as a Visible-Light Sensitive Photocatalyst. *Chemistry Letters*. 32(8): 772–773.
- Jankolovits, J., Kusoglu, A., Weber, A. Z., Dyk, A. Van, Bohling, J., Roper, J. A., Katz, A. (2016). Stable Aqueous Dispersions of Hydrophobically Modified

- Titanium Dioxide Pigments through Polyanion Adsorption: Synthesis, Characterization, and Application in Coatings. *Langmuir*. 32(8): 1929-1938.
- Jones, K. C., & Voogt, P. De. (1999). Persistent Organic Pollutants (POPs): State of the Science. *Environmental Pollution*. 100(1-3): 209-221.
- June K. Dunnick and James R. Hailey (1996). Phenolphthalein Exposure Causes Multiple Carcinogenic Effects in Experimental Model Systems. *Cancer Research*. (56): 4922-4926.
- Kavner, K. (2009). Persistent Organic Pollutants A Global Issue, A Global Response International Programs USEPA. <https://www.epa.gov/>
- Kmetyko, A., Szaniel, A., Tsakiroglou, C., Dombi, A., & Hernadi, K. (2016). Enhanced Photocatalytic H₂ Generation on Noble Metal Modified TiO₂ Catalysts Excited With Visible Light Irradiation. *Reaction Kinetics, Mechanisms and Catalysis*. 117(1): 379–390.
- Kumar, S. G., & Devi, L. G. (2011). Review on Modified TiO₂ Photocatalysis under UV/Visible Light: Selected Results and Related Mechanisms on Interfacial Charge Carrier Transfer Dynamics. *The Journal of Physical Chemistry A*. 115(46): 13211–13241.
- Lean, J. (1991). Variations in the Sun's Radiative Output. *Reviews of Geophysics*. 29(4): 505-535.
- Lei, Y., Zhang, L. D., Meng, G. W., Li, G. H., Zhang, X. Y., Liang, C. H., Wang, S. X. (2001). Preparation and Photoluminescence of Highly Ordered TiO₂ Nanowire Arrays. *Applied Physics Letters*. 78(8): 1125–1127.
- Linares-hernandez, I. (2016). A Comparative Electrochemical-Ozone Treatment for Removal of Phenolphthalein. *Journal of Chemistry*. 2016: 9.
- Linsebigler, A. L., Linsebigler, A. L., Yates Jr, J. T., Lu, G., Lu, G., & Yates, J. T. (1995). Photocatalysis on TiO₂ Surfaces: Principles, Mechanisms, and Selected Results. *Chemical Reviews*. 95(3): 735–758.
- Liu, G., Han, C., Pelaez, M., Zhu, D., Liao, S., Likodimos, V., Dionysiou, D. D. (2012). Synthesis, Characterization and Photocatalytic Evaluation of Visible

- Light Activated C-Doped TiO₂ Nanoparticles. *Nanotechnology*. 23(29): 294003.
- Liu, M., Zhou, M., Yang, H., Ren, G., & Zhao, Y. (2016). Titanium Dioxide Nanoparticles Modified Three Dimensional Ordered Macroporous Carbon for Improved Energy Output in Microbial Fuel Cells. *Electrochimica Acta*. 190: 463–470.
- Liu, S., Yu, J., & Jaroniec, M. (2011). Anatase TiO₂ with Dominant High-Energy {001} Facets: Synthesis, Properties, and Applications. *Chem. Mater.* 23: 4085–4093.
- Mahshid, S., Ghamsari, M. S., Askari, M., Afshar, N., & Lahuti, S. (2006). Synthesis of TiO₂ Nanoparticles by Hydrolysis and Peptization of Titanium Isopropoxide Solution. *Journal of Materials Processing Technology*. 65–68.
- Meng, J. F., Meng, J. G., Zhang, L. M., & Ding, L. L. (2016). Dispersion of Nano Self-Cleaning Finishing Agents about Suit Fabric. *Materials Science Forum*. 852: 356–361.
- Michaux, F., Stebe, M. J., & Blin, J. L. (2012). Microporous and Mesoporous Materials Systematic investigation of the Synthesis Parameters Driving the Preparation of Mesoporous Materials using a Nonionic Fluorinated Surfactant, 151: 201–210.
- Mills, A., Davies, R. H., Worsley, D., Goodeve, C. F., Kitchener, J. A., Pappas, S. P., Fujishima, A. (1993). Water purification by semiconductor photocatalysis. *Chemical Society Reviews*. 22(6): 417.
- Mohamed, M. A., Wan Salleh, W. N., Jaafar, J., Rosmi, M. S., Mohd. Hir, Z. A, Abd Mutalib, M., Ismail, A. F., & Tanemura, M. (2016). Carbon as Amorphous Shell and Interstitial Dopant in Mesoporous Rutile TiO₂: Bio- Template Assisted Sol-Gel Synthesis and Photocatalytic Activity. *Applied Surface Science*. 393: 46-59.
- Muthuchamy, N., Lee, K.P., & Gopalan, A.I. (2016). Enhanced Photoelectrochemical Biosensing Performances for Graphene (2D) – Titanium Dioxide Nanowire (1D) Heterojunction Polymer Conductive Nanosponges.

Biosensors and Bioelectronics. 89: 390-399.

- Nakata, K., & Fujishima, A. (2012). TiO₂ Photocatalysis: Design and Applications. *Journal of Photochemistry and Photobiology C: Photochemistry Reviews*. 13(3), 169–189.
- Neti, N. R., Misra, R., Bera, P. K., Dhodapkar, R., Bakardjieva, S., Bastl, Z., ... Bastl, Z. (2010). Synthesis of C-Doped TiO₂ Nanoparticles by Novel Sol-Gel Polycondensation of Resorcinol with Formaldehyde for Visible-Light Photocatalysis. *Metal-Organic, and Nano-Metal Chemistry*. 40: 328–332.
- Nguyen, D., Wang, W., Long, H., Shan, W., Li, X., Fang, M., Ru, H. (2016). A Facile and Controllable Multi-Templating Approach Based on a Solo Nonionic Surfactant to Preparing Nanocrystalline Bimodal Meso-Mesoporous Titania. *Microporous and Mesoporous Materials*. 230: 177–187.
- Ohtani, B., Ogawa, Y., & Nishimoto, S. (1997). Photocatalytic Activity of Amorphous - Anatase Mixture of Titanium (IV) Oxide Particles Suspended in Aqueous Solutions. *Journal of Physical Chemistry*. 5647: 3746–3752.
- Ortega-Liebana, M. C., Sanchez-Lopez, E., Hidalgo-Carrillo, J., Marinas, A., Marinas, J. M., & Urbano, F. J. (2012). A Comparative Study of Photocatalytic Degradation of 3-chloropyridine under UV and Solar Light by Homogeneous (Photo-Fenton) and Heterogeneous (TiO₂) photocatalysis. *Applied Catalysis B: Environmental*. 127: 316–322.
- Park, Y., Kim, W., Park, H., Tachikawa, T., Majima, T., & Choi, W. (2009). Environmental Carbon-doped TiO₂ Photocatalyst Synthesized without using an External Carbon Precursor and the Visible Light Activity. *Applied Catalysis B*. 91: 355–361.
- Peiro, A. M., Peral, J., Domingo, C., Domènech, X., & Ayllon, J. A. (2001). Low-temperature deposition of TiO₂ thin films with photocatalytic activity from colloidal anatase aqueous solutions. *Chemistry of Materials*. 13(8): 2567–2573.
- Pelaez, M., Nolan, N. T., Pillai, S. C., Seery, M. K., Falaras, P., Kontos, A. G., Dionysiou, D. D. (2012a). A Review on the Visible Light Active Titanium Dioxide Photocatalysts for Environmental Applications. *Applied Catalysis B:*

Environmental. 125: 331–349.

Periyat, P., Naufal, B., & Ullattil, S. G. (2016). A Review on High Temperature Stable Anatase TiO₂ Photocatalysts. *Materials Science Forum*. 855: 78–93.

Pettibone, J. M., Cwiertny, D. M., Scherer, M., & Grassian, V. H. (2008). Adsorption of Organic Acids on TiO₂ Nanoparticles: Effects of pH, Nanoparticle Size, and Nanoparticle Aggregation. *Langmuir*. 24(13): 6659–6667.

Rajkumar, Nisha, Singh, R. (2015). To Study the Effect of the Concentration of Carbon on Ultraviolet and Visible Light Photo Catalytic Activity and Characterization of Carbon. *Nanomedicine and Nanotechnology*. 6(1): 1–7.

Ratke, L., & Voorhees, P. W. (2002). *Growth and Coarsening: Ostwald Ripening in Material Processing*. Springer, Berlin; New York.

Raza, W., Haque, M. M., Muneer, M., & Bahnemann, D. (2015). Synthesis of Visible Light Driven TiO₂ Coated Carbon Nanospheres for Degradation of Dyes. *Arabian Journal of Chemistry*.

Rehman, F. U., Zhao, C., Jiang, H., & Wang, X. (2015). Biomedical Applications of Nano-Titania in Theranostics and Photodynamic therapy. *Biomaterial Science*. 4(4): 40–54.

Reunchan, P., Boonchun, A., & Umezawa, N. (2016). Electronic Properties of Highly-Active Ag₃AsO₄ Photocatalyst and Its Band Gap Modulation: An Insight from Hybrid-Density Functional Calculations. *Phys. Chem. Chem. Phys.*, 18(33): 23407–23411.

Sachs, M., Pastor, E., Kafizas, A., & Durrant, J. R. (2016). Evaluation of Surface State Mediated Charge Recombination in Anatase and Rutile TiO₂. *The Journal of Physical Chemistry Letters*. 7: 3742–3746.

Saien, J., & Mesgari, Z. (2016). Highly efficient visible-light photocatalyst of nitrogen-doped TiO₂ nanoparticles sensitized by hematoporphyrin. *Journal of Molecular Catalysis A: Chemical*. 414: 108–115.

Sakthivel, S., & Kisch, H. (2003). Daylight Photocatalysis by Carbon-Modified

- Titanium Dioxide. *Angewandte Chemie International Edition*. 42(40): 4908–4911.
- Santhi, K., Rani, C., & Karuppuchamy, S. (2016). Degradation of Alizarin Red S Dye using Ni Doped WO_3 Photocatalyst. *Journal of Materials Science: Materials in Electronics*. 27(5): 5033–5038.
- Schreiber, M., & Toyozawa, Y. (1982). Numerical Experiments on the Absorption Lineshape of the Exciton under Lattice Vibrations. III. The Urbach rule. *Journal of the Physical Society of Japan*. 51: 1544-1550.
- Schulz, H.-M., Wirth, R., & Schreiber, A. (2016). Nano-Crystal Formation of TiO_2 Polymorphs Brookite and Anatase Due To Organic-Inorganic Rock-Fluid Interactions. *Journal of Sedimentary Research*. 86(2); 59–72.
- Seo, H., Nam, S.-H., Itagaki, N., Koga, K., Shiratani, M., & Boo, J.-H. (2016). Effect of Sulfur Doped TiO_2 on Photovoltaic Properties of Dye-Sensitized Solar Cells. *Electronic Materials Letters*. 12(4): 530–536.
- Serpone, N., & Lawless, D. (1995). Size Effects on the Photophysical Properties of Colloidal Anatase TiO_2 Particles: Size quantization Versus Direct Transitions in This Indirect Semiconductor? *The Journal of Physical Chemistry*. 99(45): 16646-16654.
- Shao, X., Lu, W., Zhang, R., Pan, F., & Tio, C. (2013). Enhanced Photocatalytic Activity of TiO_2 -C Hybrid Aerogels for Methylene Blue Degradation. *Scientific Reports*. 3: 3018.
- Shi, H., Magaye, R., Castranova, V., Zhao, J., Kisin, E., Murray, A., Girard, D. (2013). Titanium Dioxide Nanoparticles: A Review of Current Toxicological Data. *Particle and Fibre Toxicology*. 10(1): 15.
- Sprong, C., Bakker, M., Niekerk, M., & Vennemann, M. (2016). Exposure Assessment of the Food Additive Titanium Dioxide (E 171) Based on use Levels Provided by the Industry. *RIVM Report 2015*. 0195.
- Tachibana, Y., Vayssieres, L., & Durrant, J. R. (2012). Artificial Photosynthesis for Solar Water-Splitting. *Nature Photonics*. 6(8): 511–518.

- Takahashi, Y., Kondo, H., Yasuda, T., Watanabe, T., Kobayashi, S.-I., & Yokohama, S. (2002). Common Solubilizers to Estimate the Caco-2 Transport of Poorly Water-Soluble Drugs. *International Journal of Pharmaceutics*. 246(1): 85–94.
- Tayyebi, A., outokesh, M., Tayebi, M., Shafikhani, A., & Şengör, S. S. (2016). ZnO Quantum Dots-Graphene Composites: Formation Mechanism and Enhanced Photocatalytic Activity for Degradation of Methyl Orange Dye. *Journal of Alloys and Compounds*. 663: 738–749.
- Than, L. D., Luong, N. S., Ngo, V. D., Tien, N. M., Dung, T. N., Nghia, N. M., ... Lam, T. D. (2017). Highly Visible Light Activity of Nitrogen Doped TiO₂ Prepared by Sol–Gel Approach. *Journal of Electronic Materials*. 46(1):158–166.
- Trengove, L. (1972). William Gregor (1761–1817) discoverer of titanium. *Annals of Science*. 29(4): 361–395.
- Tseng, T. K., Lin, Y. S., Chen, Y. J., & Chu, H. (2010). A Review of Photocatalysts Prepared by Sol-Gel Method for VOCs Removal. *International Journal of Molecular Sciences*. 11: 2336–2361.
- Uddin, M. T., Sultana, Y., & Islam, M. A. (2016). Nano-sized SnO₂ Photocatalysts: Synthesis, Characterization and Their Application for the Degradation of Methylene Blue Dye. *Journal of Scientific Research*. 8(3): 399.
- Valentin, C. Di, Pacchioni, G., Selloni, A., Uni, V., Bicocca, M., & Cozzi, V. R. (2005). Theory of Carbon Doping of Titanium Dioxide. *Chem. Mater.* 17: 6656–6665.
- Wang, D., Li, J., Zhou, G., Wang, W., Zhang, X., & Pan, X. (2016). Low Temperature Hydrothermal Synthesis of Visible-Light-Activated I-Doped TiO₂ for Improved Dye Degradation. *Journal of Nanoscience and Nanotechnology*. 16(6): 5676–5682.
- Wang, D.-H., Jia, L., Wu, X.-L., Lu, L.-Q., Xu, A.-W., Khan, S. U. M., Zhou, W. B. (2012). One-step Hydrothermal Synthesis of N-doped TiO₂/C Nanocomposites with High Visible Light Photocatalytic Activity. *Nanoscale*. 4(2): 576–584.

- Wang, L., Kumeria, T., Santos, A., Forward, P., Lambert, M. F., & Losic, D. (2016). Iron Oxide Nanowires from Bacteria Biofilm as an Efficient Visible-Light Magnetic Photocatalyst. *ACS Applied Materials & Interfaces*. 8(31): 20110–20119.
- Wang, X., Song, C., Geng, K., Zeng, F., & Pan, F. (2007). Photoluminescence and Raman Scattering of Cu-doped ZnO Films Prepared by Magnetron Sputtering. *Applied Surface Science*. 253(16): 6905-6909.
- Wang, W., Silva, C., & Faria, J (2007). Photocatalytic Degradation of Chromophore 2R using Nanocrystalline TiO₂/Activated-Carbon Composite Catalyst. *Applied Catalysis B: Environmental*. 70(1-4): 470-478.
- Wongaree, M., Chiarakorn, S., & Chuangchote, S. (2015). Photocatalytic Improvement under Visible Light in TiO₂ Nanoparticles by Carbon Nanotube Incorporation. *Journal of Nanomaterials*. 2015: 10
- Wu, X., Yin, S., Dong, Q., Guo, C., Li, H., & Kimura, T. (2013). Synthesis of High Visible Light Active Carbon Doped TiO₂ Photocatalyst by a Facile Calcination Assisted Solvothermal Method. *Applied Catalysis B: Environmental*. 142-143: 450-457.
- Xu, C., Rangaiah, G. P., & Zhao, X. S. (2014). Photocatalytic Degradation of Methylene Blue by Titanium Dioxide: Experimental and Modeling Study. *Industrial & Engineering Chemistry Research*. 53(38): 14641–14649.
- Xu, J., Yang, L., Han, Y., Wang, Y., Zhou, X., Gao, Z., Schmuki, P. (2016). Carbon-Decorated TiO₂ Nanotube Membranes: A Renewable Nanofilter for Charge-Selective Enrichment of Proteins. *ACS Applied Materials & Interfaces*.
- Xu, M., Gao, Y., Moreno, E. M., Kunst, M., Muhler, M., Wang, Y. C. (2011). Photocatalytic Activity of Bulk TiO₂ Anatase and Rutile Single Crystals Using Infrared Absorption Spectroscopy. *Physical Review Letters*. 106(13).
- Yadav, R., Waghadkar, Y., Kociok-Kohn, G., Kumar, A., Rane, S. B., & Chauhan, R. (2016). Transition Metal Ferrocenyl Dithiocarbamates Functionalized Dye-Sensitized Solar Cells with Hydroxy as an Anchoring Group. *Optical Materials*. 62:176–183.

- Yamada, Y., & Kanemitsu, Y. (2012). Determination of Electron and Hole Lifetimes of Rutile and Anatase TiO₂ Single Crystals. *Applied Physics Letters*. 101(13).
- Zaleska, A. (2008). Doped-TiO₂: A Review. *Recent Patents on Engineering*. 2(3): 157–164.
- Zhang Li. (2013). *Characterization And Visible Light Photocatalytic Activities For Environmental Remediation*. Nanyang Technological University. Ph.D. Thesis.
- Zhang, J., Dongfeng, G. H., & Zhou, L. B. (2016). Facile Route to Fabricate Carbon-Doped TiO₂ Nanoparticles and Its Mechanism of Enhanced Visible Light Photocatalytic Activity. *Applied Physics A*. 1–10.
- Zhang, P., Shao, C., Zhang, Z., Zhang, M., Mu, J., Guo, Z., Westwood, A. (2011). TiO₂@Carbon Core/Shell Nanofibers: Controllable Preparation And Enhanced Visible Photocatalytic Properties. *Nanoscale*. 3(7): 2943.
- Zhang, P., Tachikawa, T., Fujitsuka, M., & Majima, T. (2016). In Situ Fluorine Doping of TiO₂ Superstructures for Efficient Visible-Light Driven Hydrogen Generation. *ChemSusChem*. 9(6):617–623.
- Zhu, J., Chen, F., Zhang, J., Chen, H., & Anpo, M. (2006). Fe³⁺-TiO₂ Photocatalysts Prepared By Combining Sol–Gel Method With Hydrothermal Treatment And Their Characterization. *Journal of Photochemistry and Photobiology A: Chemistry*. 180(1): 196–204.